

## Specification ASTM D2000 3BA

## **EPDM Rubber**

Advantages: Excellent resistance to heat, ozone and sunlight; very good flexibility at low temperatures; good resistance to alkalis, acids and oxygenated solvents; superior resistance to water and steam.

Limitations: Poor resistance to oil, gasoline and hydrocarbon solvents; adhesion to fabrics and metals is poor.



Finish	Smooth
Powder	No
Color	Black

## **Technical Specifications**

Style#	Hardness (±5)	Tensile Strength		Elongation at break	Abrasion	Compression Set	Temperature Range (General Guidelines)		Oil Swell in ASTM oil 903
	Shore A	PSI	(min) kg/cm²	(min) %	mm³	(max) %	C°	F°	(max) %
IR301-50	50	800	55	250	-	50	-40°C to +100°C	-40°F to +212°F	-
IR303-50	50	800	55	250	-	25	-40°C to +100°C	-40°F to +212°F	-
IR301-60	60	800	55	250	-	50	-40°C to +100°C	-40°F to +212°F	-
IR303-60	60	800	55	250	-	25	-40°C to +100°C	-40°F to +212°F	-
IR301-70	70	800	55	250	-	50	-40°C to +100°C	-40°F to +212°F	-
IR303-70	70	800	55	150	-	25	-40°C to +100°C	-40°F to +212°F	

Specifications are subject to change without notice

## **Available Roll Sizes**

Thickness		Wid	dth	Length		
Inches	Inches mm		Meter	Feet	Meter	
1/16"	1.6	36 & 48	.91 & 1.2	100	30.5	
3/32"	2.4	36 & 48	.91 & 1.2	75	22.9	
1/8"	3.2	36 & 48	.91 & 1.2	50	15.3	
3/16"	4.8	36 & 48	.91 & 1.2	35	10.7	
1/4"	6.4	36 & 48	.91 & 1.2	35	10.7	
3/8"	9.5	36 & 48	.91 & 1.2	35	10.7	
1/2"	12.7	36 & 48	.91 & 1.2	25	7.6	
3/4"	19.1	36 & 48	.91 & 1.2	25	7.6	
1"	25.4	36 & 48	.91 & 1.2	25	7.6	









• Thickness and sizes per RMA tolerances

Typical Physical Properties: The typical physical properties are obtained on ASTM Test slabs and buttons; ASTM and Product Physical Values: ASTM basic requirements for physical properties are based on values obtained from standard laboratory test specimens prepared and tested in accordance with the applicable ASTM test methods. Test results from specimens prepared from finished products may not duplicate values obtained from standard test specimens. Per ASTM D300, Section 7.1, Buyers agrees that when standard test specimens are cut from finished parts in accordance with Practice D3183, a deviation to the extent of 10% on tensile strength and dongation values is permissible, Use of the ASTM Specifications. All of our here tubber products are a proprietary beined products are a proprietary beined products are a proprietary beine they been agreed and tested in accordance with Practice D3183, a deviation to the extent of 10% on tensile strength and dongation values is permissible, Use of the ASTM Specifications. In our Commercial products, the named polymer is not necessarily the polymer some products. Where appropriate, field tests may need to be performance requirements and conditions that will affect the working life of the rubber product. Where appropriate, field tests may need to be performance requirements and conditions that will affect the working life of the rubber product. Where appropriate, field tests may need to be performed before the style of sheet rubber is selected. If the customers' quality assurance includes the testing of rubber material, the test criteria should specify the physical property call outs of the ASTM specification that is most critical to its application. Polymer type along update from the selection of products (s) and or in the selection, provision, or designation of a specification is selection, provision, or designation of a specification or selection provision, or designation of a specification or designation of the selection, provision, or designation of a specification or inf

For available inventory, please contact us